

**START FORMULATION****Pigmented Floor Coating, Pigmentpowder****Component A:**

1	Epoxy Resin	CeTePox® 293 R	CTP AM / Aditya Birla
2	Defoamer	Byk® A-530	BYK Chemie
3	Pigment	Heucosin® Grey G 2229	Heubach GmbH
4	Filler	Omyacarb® 10 GU	Omya GmbH
5	Epoxy Resin	CeTePox® 293 R	CTP AM / Aditya Birla

1.04.013

35.0
0.5
2.6
55.5
6.4

100.0**Component B:**

1	Curing Agent	CeTePox® 1393 NF H	CTP AM / Aditya Birla
---	--------------	---------------------------	-----------------------

20.0

20.0**Technical Data**

Mixing Ratio	Component A : B	by weight	5 : 1
Density	Component A + B	g / ml	1.5
Viscosity (p/p, 100 s-1, @ 25°C)	Component A	mPa*s	~6000
	Component B	mPa*s	~240
	Component A + B	mPa*s	~1000
Applicable Thickness	Per Operation / Pass	mm	~1-2
Practically Usable Pot-life	At 23°C	Min.	~90

Manufacturing Instructions Component A

- Pos. 1: submitted
- Pos. 2: is added while stirring at low speed
- Pos. 3 to 4: are added one after the other at low stirrer speed, followed by stirring at higher speed for appr. 10 min. until pigment and fillers are finely dispersed
- Pos. 5: add at low stirrer speed and homogenise (appr. 5 min)

After mixing Part A and B for approximately 3-5 minutes the formulation is ready for application.

**More
Information ?**

