

**START FORMULATION****Tile Adhesive / Washable Grout (CMR-free)****Component A:**

1	Epoxy Resin	<b>CeTePox® VP 771-01 S Comp. A</b>	CTP AM / Aditya Birla
2	Thixotropic Agent	Aerosil® 202	Evonik Industries AG
3	Filler	Silica sand (0.1 - 0.2 mm)	Euroquarz GmbH
4	Pigment	Heucosin® Grey G 2229	Heubach GmbH

**Component B:**

1	Curing Agent	<b>CeTePox® VP 771-01 S Comp.B</b>	CTP AM / Aditya Birla
---	--------------	--	-----------------------

**Technical Data**

Mixing Ratio	Component A : B	by weight	100 : 8
Practically Usable Pot-life	At 23 °C	Min.	~45-60
Binder content	Component A + B	% by weight	~26
Tensile Strength	At 23 °C	MPa	>70
Flexural Strength	At 23 °C	MPa	>25

**4.01.004**20.0  
0.9  
78.5  
0.6-----  
**100.0**

8.0

-----  
**8.0****Manufacturing Instructions Component A**

- Pos. 1: submitted
- Pos. 2: is added carefully while stirring at low speed
- Pos. 3 to 4: are added one after the other at low stirrer speed, followed by stirring at higher speed for appr. 10 min. until pigment and fillers are finely dispersed

After mixing Part A and B for approximately 3-5 minutes the formulation is ready for application.

Visible grout residues on tiles can be easily cleaned with slighty acidic (acetic acid), detergent-containing water.

**More  
Information ?**